

名称: PP/PE-TD15

牌号: P221T-UV



产品简介 Product Description	主要应用 Applications
·15%矿粉填充, 弹性体增韧聚丙烯 15% talc filled and POE toughening PP	·注塑成型 Injection molding
·优异的耐UV老化性能 Excellent UV stability	·良好的机械性能 Good mechanical properties balance
·较好的耐刮擦 Good scratch resistance	·汽车内饰件的应用 Interior parts for automobile

性能 Properties	测试标准 Test Method	测试条件 Test Condition	单位 Unit	典型值 Typical Values
物理性能 Physical properties				
熔融指数 Melt Flow Rate	ISO 1133	230°C, 2.16Kg	g/10min	—
密度 Specific Gravity	ISO 1183	23°C	g/cm ³	1.02
灰份 Ash	ISO 3451	650°C,30min	%	15
机械性能 Mechanical properties				
屈服强度 Yield Strength	ISO 527	50mm/min	MPa	22
屈服伸长率 Elongation at Yield	ISO 527	50mm/min	%	5
拉伸模量 Tensile Modulus	ISO 527	1mm/min	MPa	—
弯曲模量 Flexural Modulus	ISO 178	2mm/min	MPa	1300
简支梁缺口冲击强度 Notched Charpy Impact Strength	ISO 179-1eA	23°C	kJ/m ²	30
简支梁缺口冲击强度 Notched Charpy Impact Strength	ISO 179-1	23°C	kJ/m ²	25
其它性能 Other properties				
热变形温度 Heat deflection temperature	ISO 75	0.45MPa	°C	—
		1.80MPa	°C	—
维卡软化温度 Vicat Softening Temp.	ISO 306	50N	°C	—
收缩率 Mold Shrinkage	internal test method	flow direction	%	0.70-0.90
		cross flow direction	%	1.10-1.30
阻燃性 Flammability	TL1010	—	mm/min	34

说明: 以上数据是典型值, 不是保证值。根据模具设计, 例如浇口类型, 浇口分布, 浇口数量的不同, 注塑工艺和制件厚度的不同, 测试结果会有波动。不同的颜色, 测试结果也会有波动。在使用材料之前, 请咨询旭光聚合物有限公司。

Note: The data above is typical value for reference, not guarantee value. The data will vary with tool design such as gate type, gate location, gate number, injection molding process and part thickness. The data will vary with different color as well. Prior to use the material, please consult with Sunway polymer.

典型加工条件 Processing Conditions		参考范围 Range
熔体温度 Melt Temperature		200-230°C
料筒温度 Barrel Temperature	后段, Rear	200--210°C
	中段, Center	210--220°C
	前段, Front	220--230°C
模具温度 Mold Temperature		70-80°C
预干燥 Pre-Dry needed		90-100°C, 2-4h

说明: 以上数值仅供注塑机参考使用, 可根据不同机型、不同模具以及产品要求, 对上述工艺做适当调整。

Note: The above process condition is only for reference. The actual process should be adjusted according to different type of machine, mold design and product design.